

## Specification of Bitumen Penetration 100/150

Bitumen 100/150	Test method	Unit	Specification
Penetration @ 25°C	IP 49	mm/10	100/150
Softening point °C	IP 58	°C	39/47
Resistance to hardening at 163°C			
Change of mass		%	0.8
Retained penetration	IP 49	%	43 min
Softening point after hardening	IP 58	°C	41
Flashpoint °C	IP 36	°C	230 min
Solubility	IP 47	wt %	99 min
Kinematic Viscosity @ 135°C	IP 370	mm <sup>2</sup> /s	175 min



No303,Navab Complex,Navab St,  
Isfahan,Iran



[www.rahabitumen.com](http://www.rahabitumen.com)



+983132355214



[info@rahabitumen.com](mailto:info@rahabitumen.com)