

Specification of Bitumen Penetration 20/30

Bitumen 20/30	Test method	Unit	Specification
Penetration @ 25°C	EN 1426	mm/10	20/30
Softening point °C	EN 1427	°C	53/65
Kinematic Viscosity @ 135°C	EN 12595	mm ² /s	530 min
Flashpoint °C	EN 22592	°C	240 min
Solubility in CS ₂ (wt) %	EN 12592	wt %	99 min



No303, Navab Complex, Navab St,
Isfahan, Iran



www.rahabitumen.com



+983132355214



info@rahabitumen.com