

## Specification of Bitumen Penetration 200/300

Bitumen 200/300	Test method	Unit	Specification
Specific gravity @ 25°C	ASTM D70	Kg/cm <sup>3</sup>	990-1040
Penetration @ 25°C	ASTM D5	mm/10	200/300
Softening point °C	ASTM D36	°C	32
Ductility @25 °C	ASTM D113	cm	100 min
Loss on heating(wt) %	ASTM D6	wt %	1 max
Drop in penetration after heating %	ASTM D5-D6	%	37 min
Flashpoint °C	ASTM D92	°C	177 min
Solubility in Trichloroethylene	ASTM D2042	wt %	99 min
Spot test	A.A.S.H.O.T102	---	Negative



No303,Navab Complex,Navab St,  
Isfahan,Iran



[www.rahabitumen.com](http://www.rahabitumen.com)



+983132355214



[info@rahabitumen.com](mailto:info@rahabitumen.com)