

Specification of Bitumen Penetration 85/100

Bitumen 85/100	Test method	Unit	Specification
Specific gravity @ 25°C	ASTM D70	Kg/cm ³	1.01/1.06
Penetration @ 25°C	ASTM D5	mm/10	85/100
Softening point °C	ASTM D36	°C	41/49
Ductility @25 °C	ASTM D113	cm	100 min
Loss on heating(wt) %	ASTM D6	wt %	0.2 max
Drop in penetration after heating %	ASTM D5-D6	%	20 max
Flashpoint °C	ASTM D92	°C	250 min
Solubility is CS ₂ (wt) %	ASTM D4	wt %	99 min
Spot test	A.A.S.H.O.T102	---	Negative



No303,Navab Complex,Navab St,
Isfahan,Iran



www.rahabitumen.com



+983132355214



info@rahabitumen.com