

Specification of oxidized bitumen 115/15

Bitumen 115/15	Test method	Unit	Specification
Specific gravity @25/25 C	ASTM D70	(Kg/m3)	1.05 approx.
Penetration @ 25°C	ASTM D5	mm/10	10/20
Softening point °c	ASTM D36	°C	110/120
Loss on heating(wt) %	ASTM D6	Wt. %	0.2 max
Flashpoint c	ASTM D92	°C	250 min
Solubility is CS2(wt) %	ASTM D4	Wt. %	99.5 max
Stop test	A.a.s.h.o.t102	----	nagative



No303,Navab Complex,Navab St,
Isfahan,Iran



www.rahabitumen.com



+983132355214



info@rahabitumen.com