

## Specification of oxidized bitumen 85/40

Bitumen 85/40	Test method	Unit	Specification
Specific gravity @25/25 C	ASTM D70	(Kg/m3)	1.05 approx.
Penetration @ 25°C	ASTM D5	mm/10	35/40
Softening point °c	ASTM D36	°C	80/90
Loss on heating(wt) %	ASTM D6	Wt. %	0.2 max
Flashpoint c	ASTM D92	°C	250 min
Solubility in CS <sub>2</sub> (wt) %	ASTM D4	Wt. %	99.5 max
Stop test	A.A.S.H.O.T102	---	negative



No303,Navab Complex,Navab St,  
Isfahan,Iran



[www.rahabitumen.com](http://www.rahabitumen.com)



+983132355214



[info@rahabitumen.com](mailto:info@rahabitumen.com)