

# Specification of Cutback Bitumen **RC-30**

Type: **Rapid-Curing**

Property	Min	Max	Test Method
Kinematic viscosity at 60°C (140°F), cST	30	60	ASTM D2170
Flash point (tag open cup), °C (°F)	—	—	ASTM D3143
<b>Distillate test</b>			
<b>Distillate, volume percent of total Distillate to 680°F (360°C)</b>			
to 374°F (190°C)	15	—	ASTM D402
to 437°F (225°C)	55	—	ASTM D402
to 500°F(260°C)	75	—	ASTM D402
to 600°F (315°C)	90	—	ASTM D402
Residue from distillation to 680°F (360°C), percent volume by difference	50	—	ASTM D402
<b>Test on Residue from distillation test</b>			
Penetration 77°F (25°C) 100g,5s mm	80	120	ASTM D5
Ductility 77°F (25°C) 5cm/min cm	100	—	ASTM D113
Solubility in trichloroethylene %	99	—	ASTM D2042
Water, percent volume	—	0.2	ASTM D95



No303,Navab Complex,Navab St,  
Isfahan,Iran



[www.rahabitumen.com](http://www.rahabitumen.com)



+983132355214



[info@rahabitumen.com](mailto:info@rahabitumen.com)