

Specification of Anionic Bitumen Emulsion **HFMS-2s**

Property	Min	Max	Test Method
Viscosity, Saybolt Furol at 25 °C, SFS	50	—	ASTM D244
Storage stability test, 24-h, %	—	1	ASTM D6930
Particle charge test	minus		ASTM D244
Sieve test, %	—	0.1	ASTM D6933
Distillation:			
Residue, %	65	—	ASTM D244
Solvents, by volume of emulsion	1	7	ASTM D6997
Test on Residue from distillation test:			
Float test, 60 degrees Celsius, s	1200	—	ASTM D139
Penetration 77°F (25°C) 100g,5s mm	200	—	ASTM D5
Ductility 77°F (25°C) 5cm/min cm	40	—	ASTM D113
Solubility in trichloroethylene %	97.5	—	ASTM D2042



No303,Navab Complex,Navab St,
Isfahan,Iran



www.rahabitumen.com



+983132355214



info@rahabitumen.com