

## Specification of Anionic Bitumen Emulsion MS-2

Property	Min	Max	Test Method
Viscosity, Saybolt Furol at 25 °C, SFS	20	100	ASTM D244
Storage stability test, 24-h, %	—	1	ASTM D6930
Particle charge test	minus		ASTM D244
Sieve test, %	—	0.1	ASTM D6933
<b>Distillation:</b>			
Residue, %	65	—	ASTM D244
<b>Test on Residue from distillation test:</b>			
Penetration 77°F (25°C) 100g,5s mm	100	200	ASTM D5
Ductility 77°F (25°C) 5cm/min cm	40	—	ASTM D113
Solubility in trichloroethylene %	97.5	—	ASTM D2042



No303,Navab Complex,Navab St,  
Isfahan,Iran



[www.rahabitumen.com](http://www.rahabitumen.com)



+983132355214



[info@rahabitumen.com](mailto:info@rahabitumen.com)