

Specification of viscosity grade bitumen **AR-8000**

Tests on Residue from Rolling Thin-Film Oven	Units	Specification
Viscosity, 140°F (60°C)	p	8000± 2000
Viscosity, 275°F (135°C), Min	cSt	400
Penetration, 77°F (25°C), 100g, 5sec	0.1 MM	20
Penetration, 77°F (25°C), 100g, 5sec, Min	0.1 MM	50
Ductility at 25°C, cm, min	CM	75
Tests on original asphalt		
Flash point, °C, min	°C	232
Solubility in Trichloroethylene, %, min	%Wt	99



No303,Navab Complex,Navab St,
Isfahan,Iran



www.rahabitumen.com



+983132355214



info@rahabitumen.com