



RAHA SADR INDUSTRIAL CO

BPP modified bitumen roll sheet

RAW	TEST	UNIT	BOF	BPP	
1	Length	M	10	10	
2	Width	M	1	1	
3	Thickness	mm	4±0.2	4±0.2	
4	Mass per unit area	Kg/m ²	4.1±0.2	4.1±0.2	
5	Water permeability (min)	KPa	60	60	
6	Heat stability	Cool local	C	100	100
		tropical	C	90	
7		Cool local	C	-5	+5
		Tropical	C	+5	0
8	water absorption	Absorbed(max)	%	-	1
		Loss(max)	%	-	1
9	Tear resistance	longitudinal	kgf	12	12
		transverse	kgf	10	12



Unit303,Navab Complex,
Navab Safavi St.,Esfahan-Iran



+983132355207
+983132355214



www.rahabitumen.com



info@rahabitumen.com